

# **High Performance PEM Fuel Cells - From Electrochemistry and Material Science to Engineering Development of a Multicell Stack**

Monthly report, MR #19

July 1996

ONR Contract # N00014-95-1-0114

Submitted by:

A. John Appleby and Supramaniam Srinivasan

Principal and Co-principal Investigators


Center for Electrochemical Systems and Hydrogen Research  
Texas Engineering Experiment Station  
Texas A&M University System  
238 Wisenbaker Building  
College Station, Texas 77843-3402

Submitted to:

Dr. Lawrence H. Dubois  
Defense Sciences Office  
Advanced Research Projects Agency  
3701 N. Fairfax Drive  
Arlington, VA 22203-1714

Dr. Robert J. Nowak  
Code 313  
Office of Naval Research  
Ballston Tower One  
800 North Quincy Street  
Arlington, Virginia 22217-5660

Mr. Jay Stedman  
10 Harvest Lane  
Glastonbury, CT 06033



September 4, 1996

DTIC QUALITY INSPECTED 3

19970513 026

## TABLE OF CONTENTS

<b>1. Task 1. Advanced Membrane - Electrode Assembly (MEA) Optimization</b>	<b>4</b>
1.1 Catalysts and Electrodes	4
1.2 Proton Conducting Membranes	4
1.3 Work to be Performed in the Next Month	4
<b>2. Task 2. Water Management</b>	<b>5</b>
2.1 Single Cells	5
2.2 Cell Stacks	5
2.3 Work to be Performed in the Next Month	5
<b>3. Task 3. Lightweight Cell Components</b>	<b>6</b>
3.1 Compact Lightweight Bipolar Plates	6
3.2 Work to be Performed During Next Month	7
<b>4. Task 4: Performance Demonstration in &gt; 250 W Short Stack</b>	<b>7</b>
4.1. Work to be Performed in the Next Quarter	7
<b>Summary of Expenditures</b>	<b>7</b>

## LIST OF FIGURES

- Figure 1 Cell potential vs. current density plots for PEMFCs for identically prepared MEAs, 50 cm<sup>2</sup> cell, anode Pt loading 0.3 mg/cm<sup>2</sup>, cathode Pt loading 1.4 mg/cm<sup>2</sup> GORE-SELECT™ 40 μm membrane, temperature 50 °C, atmospheric pressure, reactants humidified. 8
- Figure 2 Potential vs current density plots for an MEA tested in cell fixtures with different gas flow field design. 50 cm<sup>2</sup> cell, anode Pt loading 0.3 mg/cm<sup>2</sup>, cathode Pt loading 1.2 mg/cm<sup>2</sup>, GORE-SELECT 40 μm membrane, temperature 50 °C, atmospheric pressure, reactants humidified. 8
- Figure 3 Summary of expenditures - monthly and running totals. 9

# **High Performance PEM Fuel Cells: From Electrochemistry and Material Science to Engineering Development of a Multicell Stack**

## **1. Task 1. Advanced Membrane - Electrode Assembly (MEA) Optimization**

Investigators: Serguey Gamburzev and Omourtag A. Velev

### Objectives

The objective of this Task is to develop MEAs capable of attaining a current density of 0.7 A/cm<sup>2</sup> at 0.7 V with hydrogen and air as reactants at atmospheric pressure.

### **1.1 Catalysts and Electrodes**

Several 50 cm<sup>2</sup> MEAs were prepared to test the reproducibility of our techniques for electrodes and MEAs manufacture. Results from these tests are presented on Figure 1. At low current densities the performance of the cells is identical. In the range of current densities of practical interest differences of up to 40 mV can be observed.

### **1.2 Proton Conducting Membranes**

We used different thicknesses GORE-SELECT™ and Nafion® 112 membrane.

### **1.3 Work to be Performed in the Next Month**

- Preparation of larger size electrodes (up to 200 cm<sup>2</sup>) with the best electrode composition and determination of the effects of scale-up on cell performance.

## **2. Task 2. Water Management**

Investigators: Hari Dhar\*, Serguey Gamburzev, Omourtag A. Velev, and Frank Simoneaux

### Objectives

The objective of this Task is to eliminate external humidification of the reactant gases for PEMFC stacks operating at the desired current density of  $0.7 \text{ A/cm}^2$  for which the goal is a cell potential of 0.7 V.

### **2.1 Single Cells**

No single cell tests were performed this month.

### **2.2 Cell Stacks**

During this month a four cell stack with MEAs provided by BCS Technology was assembled and tested. The MEAs were with electrodes with catalyst loading of  $4.5 \text{ mg Pt/cm}^2$ , area  $50 \text{ cm}^2$ , and Nafion® 112 membrane. The uncatalyzed gas diffusion substrate for these MEAs was provided by CESH. The cell stack was operated with dry reactant gases at atmospheric pressure and at  $50^\circ\text{C}$  continuously for 600 hours at different power levels. The average cell voltage at a current density of  $300 \text{ mA/cm}^2$  was 0.61 V.

### **2.3 Work to be Performed in the Next Month**

#### **2.3.1 Single Cells**

- Evaluation of thinner membranes such as Nafion 112 and GORE-SELECT™.

---

\* BCS Technology, Inc. - subcontractor on this project

- Evaluation of self-humidified MEAs with Nafion 112 and GORE-SELECT™ membranes in larger (100 and 150 cm<sup>2</sup>) area fuel cells. The objective will be to reproduce the performance of smaller cells.

### **2.3.2 Cell Stacks**

- Investigation of the effect of scale-up and cell stacking on performance in four cell stacks using BCS and CESHRE MEAs.

## **3. Task 3. Lightweight Cell Components**

Investigators: Imran J. Kakwan, Frank Simoneaux, and Omourtag A. Velev

### Objectives

The objective of this Task is to identify and test cell components to build a lightweight PEMFC stack.

### **3.1 Compact Lightweight Bipolar Plates**

A study on the effect of gas flow field design on fuel cell performance was initiated this month. One MEA prepared with 40 µm thick membrane GORE-SELECT™ and CESHRE electrodes was tested in two types of flow fields. One with three serpentine channels in series (series design) and one with three channels in a series/parallel configuration (series/parallel design). Comparison of the cell performance is presented on Figure 2. There is very little difference in cell performance. At high current densities the series/parallel design shows a slight advantage over the series design. We used real time neutron radiography to image liquid water flow patterns during cell operation. This technique provides us with a quick and reliable indicator for the quality of the flow field design. The series design showed no water

accumulation and channel plugging during operation at different power levels. We observed that some of the channels in the series/parallel design became plugged with water soon after cell startup and remained full with water during the cell operation. This is probably due to the uneven gas flow distribution for this design.

### **3.2 Work to be Performed During Next Month**

- Flow field design optimization
- Real time neutron radiography experiments

### **4. Task 4: Performance Demonstration in > 250 W Short Stack**

Investigators: James Lee, Imran J. Kakwan, and Omourtag A. Veleev.

Status - no work during quarter.

#### **4.1. Work to be Performed in the Next Quarter**

- Studies and analysis of designs for bipolar plates, flow-fields, thermal and water management for a short stack configuration will continue.

### **Summary of Expenditures**

The summary of expenditures for this project is presented in Figure 3.




Figure 1 Cell potential vs. current density plots for PEMFCs for identically prepared MEAs, 50 cm<sup>2</sup> cell, anode Pt loading 0.3 mg/cm<sup>2</sup>, cathode Pt loading 1.4 mg/cm<sup>2</sup> GORE-SELECT™ 40 μm membrane, temperature 50 °C, atmospheric pressure, reactants humidified.




Figure 2 Potential vs. current density plots for an MEA tested in cell fixtures with different gas flow field design. 50 cm<sup>2</sup> cell, anode Pt loading 0.3 mg/cm<sup>2</sup>, cathode Pt loading 1.2 mg/cm<sup>2</sup>, GORE-SELECT 40 μm membrane, temperature 50 °C, atmospheric pressure, reactants humidified.






Figure 3 Summary of expenditures - monthly and running totals.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE Sept 4, 1996	3. REPORT TYPE AND DATES COVERED Monthly Report - July 1996		
4. TITLE AND SUBTITLE High Performance PEM Fuel Cells From Electrochemistry and Material Science to Engineering Development of a Multicell Stack			5. FUNDING NUMBERS G-N00014-95-1-0114	
6. AUTHOR(S) A. John Appleby and Supramaniam Srinivasan				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Center for Electrochemical Systems and Hydrogen Research, Texas Engineering Experiment Station, Texas A&M University System, College Station, TX 77843-3402			8. PERFORMING ORGANIZATION REPORT NUMBER MR #19	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of the Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5660			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)				
<p>Several 50 cm<sup>2</sup> MEAs were prepared to test the reproducibility of our techniques for electrodes and MEAs manufacture. At low current densities the performance of the cells is identical. In the range of current densities of practical interest differences of up to 40 mV can be observed.</p> <p>During this month a four cell stack with MEAs provided by BCS Technology was assembled and tested. The MEAs were with electrodes with catalyst loading of 4.5 mg Pt/cm<sup>2</sup>, area 50 cm<sup>2</sup>, and Nafion<sup>®</sup> 112 membrane. The uncatalyzed gas diffusion substrate for these MEAs was provided by CESH. The cell stack was operated with dry reactant gases at atmospheric pressure and at 50 °C continuously for 600 hours at different power levels. The average cell voltage at a current density of 300 mA/cm<sup>2</sup> was 0.61 V.</p>				
14. SUBJECT TERMS PEMFC, fuel cells			15. NUMBER OF PAGES 9	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICATION OF ABSTRACT	20. LIMITATION OF ABSTRACT	